

Amendments to the claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of claims:

- OK to enter
1. (Currently amended): A white, biaxially oriented film with a thickness in the range from 10 to 500 μm and a whiteness of 90 % or more, whose main constituent is at least one crystallizable thermoplastic and which comprises at least one rutil-type titanium dioxide as white pigment and at least one optical brightener and at least one soluble blue dye, with or without other additives, and has also at least one other functionality.
2. (Original): The film as claimed in claim 1, wherein the crystallizable thermoplastic is a polyethylene terephthalate, polybutylene terephthalate, polyethylene naphthalate, bibenzoyl-modified polyethylene terephthalate, or a mixture of these.
3. (Original): The film as claimed in claim 1, wherein the concentration of the white pigment present is in the range from 2.0 to 25.0% by weight based on the weight of the thermoplastic.
4. (Original): The film as claimed in in claim 1, wherein the optical brightener present comprises at least one benzoxazole derivative, triazine derivative, phenylcoumarin derivative, or bisstearyl biphenyl derivative, in amounts of from 10 to 50 000 ppm based on the weight of the crystallizable thermoplastic.
5. (Currently amended): The film as claimed in in claim 1, which has gained at least one other functionality by being provided with a flame retardant and/or with UV stabilizers (UV absorbers), and/or has been coated so as to be sealable, and/or has been coated on one or both surfaces, and/or has been corona-treated on one or both sides[, and has been provided with a soluble dye alongside with the optical brightener].
- B1

6. (Original): The film as claimed in claim 5, wherein the concentration of the UV absorber is in the range from 0.01 to 5.0% by weight, and the concentration of the soluble dye is in the range from 10 to 10 000 ppm.

7. (Original): The film as claimed in claim 5, wherein the UV absorbers present are 2-hydroxybenzophenones, 2-hydroxybenzotriazoles, organonickel compounds, salicylic esters, cinnamic ester derivatives, resorcinol monobenzoates, oxanilides, hydroxybenzoic esters, sterically hindered amines, or triazines, preferably 2-hydroxybenzotriazoles or triazines, or in particular 2-(4,6-diphenyl-1,3,5-triazin-2-yl)-5-hexyloxyphenol or 2,2'-methylenebis(6-(2H-benzotriazol-2-yl)-4-(1,1,2,2-tetramethylpropyl)phenol).

8. (Original): The film as claimed in claim 5, wherein the flame retardant present is an organic phosphorus compound.

9. (Original): The film as claimed in claim 8, wherein the organic phosphorus compound is a carboxyphosphinic acid or anhydride thereof.

10. (Currently amended): The film as claimed in claim 8, wherein the organic phosphorus compound is bis(5-ethyl-2-methyl-2-oxo-2λ⁵-[1,3,2]dioxaphosphinan-5-ylmethyl)-methanephosphonate.

11. (Original): The film as claimed in claim 1, wherein a hydrolysis stabilizer is present, in the form of phenolic stabilizers, alkali metal/alkaline earth metal stearates, and/or alkali metal/alkaline earth metal carbonates, in amounts of from 0.01 to 1.0% by weight.

12. (Original): The film as claimed in claim 11, wherein the phenolic stabilizer is present in amounts of from 0.05 to 0.6% by weight and having a molar mass above

500 g/mol.

13. (Original): The film as claimed in claim 1, wherein regrind is present.
14. (Withdrawn): A process for producing a white, biaxially oriented film with a thickness in the range from 10 to 500 μm whose main constituent is at least one crystallizable thermoplastic, which comprises extruding a crystallizable thermoplastic with at least one rutile-type titanium dioxide as white pigment and with at least one optical brightener, and with other substances providing functionality, to give a flat melt film, quenching and solidifying the same with the aid of a chill roll to give substantially amorphous prefilm, then reheating this film and stretching the same at least once longitudinally and transversely, then heat-setting the film at temperatures of from 200 to 280° C, and finally cooling and winding up the film.
15. (Withdrawn): The process as claimed in claim 14, wherein the film is given at least one other functionality by being provided with a flame retardant and/or with UV stabilizers and/or with at least one sealable layer, and/or by being coated on one or both surfaces, and/or by being corona-treated on one or both sides, and has a soluble dye alongside the optical brightener.
16. (Withdrawn): The process as claimed in claim 14, wherein the film is produced by metering the rutile-type titanium dioxide, the optical brightener, and the other substances providing functionality into the extruder.
17. (Withdrawn): The process as claimed in claim 16, wherein the rutile-type titanium dioxide, the optical brightener, and the other substances are added by way of masterbatch technology.
18. (Withdrawn): The process as claimed in claim 14, wherein use is made of regrind.

- B2
19. (New): The film as claimed in claim 1, wherein the dye is present in an amount of from 10 to 10,000 ppm, based on the weight of the crystallizable thermoplastics.
 20. (New): The film as claimed in claim 19, wherein the blue dye is Sudan Blue 2.
 21. (New): The film as claimed in claim 1, wherein the crystallizable thermoplastic has a polyethylene glycol content of 1 % by weight or more and the film is thermoformable.

Dated: Sept. 29, 2003

Respectfully submitted

K. Schweitzer

Klaus Schweitzer
see attached Limited Recognition
Under 37 C.F.R. § 10.9 (b)

ProPat, L.L.C.
2912 Crosby Road
Charlotte, NC 28211
Phone (704) 365-4881
Fax (704) 365-4851

RECEIVED
CENTRAL FAX CENTER
SEP 29 2003

OFFICIAL


**BEFORE THE OFFICE OF ENROLLMENT AND DISCIPLINE
UNITED STATES PATENT AND TRADEMARK OFFICE**

LIMITED RECOGNITION UNDER 37 CFR § 10.9(b)

Klaus Schweitzer is hereby given limited recognition under 37 CFR § 10.9(b) as an employee of ProPat, L.L.C. to prepare and prosecute U.S. patent applications wherein the applicant is the client of ProPat, L.L.C., and the attorney of record in the applications is Mr. Gregory Clements (Reg. No. 30,713). This limited recognition shall expire on the date appearing below, or when whichever of the following events first occurs prior to the date appearing below: (i) Klaus Schweitzer ceases to lawfully reside in the United States, (ii) Klaus Schweitzer's employment with ProPat, L.L.C. ceases or is terminated, or (iii) Klaus Schweitzer ceases to remain or reside in the United States on an E2 visa.

This document constitutes proof of such recognition. The original of this document is on file in the Office of Enrollment and Discipline of the U.S. Patent and Trademark Office.

Expires: November 13, 2003


Harry I. Moatz

Director of Enrollment and Discipline

**RECEIVED
CENTRAL FAX CENTER**

SEP 29 2003

OFFICIAL